



中国认可
国际互认
检测
TESTING
CNAS L4350



检验检测报告

TEST REPORT

No.: MC228-240184*

样品名称 Sample Name	浴室柜用饰面胶合板 Surface decorated plywood of Essential Vanity
型号规格 Model Specification	36478T, 500mm×500mm×18mm
委托单位 Applicant	科勒（中国）投资有限公司 KOHLER CHINA INVESTMENT CO., LTD
检验类别 Test Type	普通送样 Common Sample

上海建科检验有限公司

Shanghai Jianke Technical Assessment of Construction Co.,Ltd.





中国认可
国际互认
检测
TESTING
CNAS L4350

上海建科检验有限公司

Shanghai Jianke Technical Assessment of Construction Co.,Ltd.

检验检测报告

TEST REPORT

检验类别: 普通送样
Test Type: Common Sample
委托编号: MC22-240402
Contract No.

报告编号: MC228-240184*
Report No.

第1页共3页
Page 1 of 3

委托单位 Applicant	科勒 (中国) 投资有限公司 KOHLER CHINA INVESTMENT CO., LTD	联系方式 Contact Information	021-26096207
单位地址 Address	上海宝山区丰翔路1955号 No. 1955 Fengxiang Road, Baoshan District, Shanghai	委托日期 Contract Date	2024-05-08
样品名称 Sample Name	浴室柜用饰面胶合板 Surface decorated plywood of Essential Vanity	样品编号 Sample No.	MC22-240402-01
生产单位 Manufacturer	科勒 (中国) 投资有限公司 KOHLER CHINA INVESTMENT CO., LTD	生产日期 Manufacture Date	2024.4
型号规格 Model Specification	36478T, 500mm×500mm×18mm	批号 Batch number	--
样品数量 Quantity	10块 10pieces	代表数量 Batch Quantity	--
商 标 Trade	科勒Kohler	到样日期 Received Date	2024-05-08
样品状态 Sample Status	外观无异常 No abnormal appearance		
判定依据 Judgement Reference	GB/T 34722-2017 《浸渍胶膜纸饰面胶合板和细木工板》 GB/T 34722-2017 Surface decorated plywood and blockboards with paper impregnated thermosetting resins		
检验日期 Test Date	2024-05-16~2024-05-24	签发日期 Date Of Issue	2024-08-16
检验地点 Test Address	上海市申富路568号 No.568 Shen Fu Road, Shanghai		
检验结论 Test Conclusion	送检的样品经检验, 按上述判定依据的技术指标判定为所检项目合格。 The tested samples shall be judged to be qualified according to the technical indexes mentioned above. 检验机构 (盖章) Organization (Stamp)		
备 注 Remarks	1、委托方声明: 35551T-MLR; 35551T-MSC; 35974T-MLR; 35974T-MSC; 35980T-MLR; 35980T-MSC; 35981T-MLW; 35981T-MPR; 35982T-MLW; 35982T-MPR; 36457T-MLW; 36457T-MPR; 36478T-MLW; 36478T-MPR; 36479T-MLW; 36479T-MPR; 36484T-MLW; 36484T-MPR; 以上型号产品为同种材料, 同种工艺结构, 仅尺寸、花色上不同。 Client states: 35551t-mlr; 35551t-msc; 35974t-mlr; 35974t-msc; 35980t-mlr; 35980t-msc; 35981t-mpr; 35982t-mlw; 35982t-mpr; 36457t-mlw; 36457t-mpr; 36478t-mlw; 36479t-mpr; 36484t-mlw; 36484t-mpr; the above products are of the same material and process structure, only different in size and color. 2、委托方声明: 样品结构为9层全桉木。 Client's statement: the sample structure is 9 layers of eucalyptus.		

批准: 张治宇

审核: 杨旭

编制: 伏家君

Approved by

Checked by

Compiled by

上海建科检验有限公司

Shanghai Jianke Technical Assessment of Construction Co.,Ltd.

检验检测报告

TEST REPORT

检验类别: 普通送样
Test Type: Common Sample

委托编号: MC22-240402
Contract No.

报告编号: MC228-240184*
Report No.

第2页共3页
Page 2 of 3

检测结果汇总 Test Results Summary						
序号 No.	检测项目 Test Item(s)		标准值 Requirement of Standard	检测结果 Test Result	检测方法 Test Method	单项判定 Judgement
1	含水率, % Moisture Content		4.0~16.0	8.5	GB/T 17657-2013	合格 Qualified
2	胶合强度, MPa Bonding strength		≥0.70MPa的合格试件数 等于或大于试件总数 的90% (有效试件数占试 件总数一半以上) The number of qualified specimens ≥0.70 MPa is equal to or greater than 90% of the total specimens (the number of effective specimens is more than half of the total specimens)	≥0.70MPa的合格试件数 占试件总数的100% (有 效试件数占试件总 数100%) The number of qualified specimens ≥ 0.70 MPa accounted for 100% of the total specimens (the number of effective specimens accounted for 100% of the total specimens)	GB/T 17657-2013	合格 Qualified
3	表面胶合强度, MPa		≥0.60	0.94	GB/T 17657-2013	合格 Qualified
4	表面耐划痕 Surface resistant to scratches		≥1.5N表面无大于90%的 连续划痕 No more than 90% continuous scratches on ≥1.5 N surface	1.5N表面无大于90%的连 续划痕 1.5 N surface without more than 90% continuous scratches	GB/T 17657-2013	合格 Qualified
5	表面耐磨 Wear resistant surface	磨 耗值, mg/100r Attrition value	≤80	59	GB/T 17657-2013	合格 Qualified
		表面情况 On the surface	磨100r之后留有花纹且不 露底 After grinding for 100R, it leaves a pattern and does not show its bottom	磨100r之后留有花纹且不 露底 After grinding for 100R, it leaves a pattern and does not show its bottom		合格 Qualified
6	表面耐干热 Surface resistant to dry heat		达到4级以上 Level 4 or above	5级 Level 5	GB/T 17657-2013	合格 Qualified
7	表面耐污染腐蚀 The surface is resistant to contamination and corrosion		达到5级 Level 5	5级 Level 5	GB/T 17657-2013	合格 Qualified

上海建科检验有限公司
Shanghai Jianke Technical Assessment of Construction Co.,Ltd.
检验检测报告
TEST REPORT

检验类别: 普通送样
Test Type: Common Sample

委托编号: MC22-240402
Contract No.

报告编号: MC228-240184*
Report No.

第3页共3页
Page 3 of 3

检测结果汇总 Test Results Summary					
序号 No.	检测项目 Test Item(s)	标准值 Requirement of Standard	检测结果 Test Result	检测方法 Test Method	单项判定 Judgement
8	表面耐冷热循环 Surface resistance to cold and heat cycles	无裂纹、鼓泡、变色、起皱等 No crack, bubbling, discoloration, wrinkling, etc	无裂纹、鼓泡、变色、起皱等 No crack, bubbling, discoloration, wrinkling, etc.	GB/T 17657-2013	合格 Qualified
9	表面耐龟裂 Surface resistant to cracking	达到4级以上 Level 4 or above	5级 Level 5	GB/T 17657-2013	合格 Qualified
10	表面耐水蒸气 The surface is resistant to water vapor	达到4级以上 Level 4 or above	5级 Level 5	GB/T 17657-2013	合格 Qualified
11	耐光色牢度 Color fastness to light	大于或等于灰度卡4级 Greater than or equal to gray card grade 4	> 灰度卡4级 > Gray card level 4	GB/T 17657-2013	合格 Qualified
说 明 Declaration		1、本报告代替原报告MC228-240184。 This report replaces the original report MC228-240184.			

(本报告内容结束)
(End of Report)

联系方式: 上海市申富路568号 (邮编: 201108) 021-54428584 / 54425584

JC/BG 8-226-2022

Contacts: No.568 Shenfu Road, Shanghai (Zip:201108) 021-54428584/54425584

声 明: 1、以上结果委托单位如有异议, 请在报告收到之日起十五日内提出。

Statement: If Applicant has any question about the testing result above, please inform us within 15 days after receiving the report.

2、报告未经本机构同意, 不得部分复制本报告。

This report shall not be partially copied without our permission.

3、本机构不负责委托方所提供样品相关信息及企业信息真实性的证实。

This report is not responsible for the confirmation of sample information and enterprise information provided by the applicant.

4、送样检验结果仅对来样负责。

Unless otherwise stated, the results shown in this report refer only to the sample(s) tested.

5、本报告以中文为准。

Only the Chinese version report is the official version.